



**Thermo**  
ELECTRON CORPORATION  
*Karl Fischer Titrator*

Log # **KF1246**

**Overview**

---

**Sample** TEXTILES - WOOL

**Industry** TEXTILES

**Group Number** 28

**Typical moisture** 10%

**Sample size** 3.0g

**Summary of  
procedure**

Method Parameters

<b>Instrument</b>	AF8 Volumetric Karl Fischer	<b>Titration Current</b>	
<b>Volumetric Reagent</b>	Reidel de Haen Composite 5	<b>Endpt Rate</b>	
<b>Volumetric Solvent</b>	MEOH	<b>Stirrer/blender speed</b>	5
<b>Pump Tubing</b>	SILICONE	<b>Extract time</b>	
<b>Vessel/Vessel Tubing</b>	LARGE	<b>Mode of analysis</b>	SAMPLE ONLY
<b>Endpt/Step Level</b>	8/5	<b>Vaporizer oven</b>	
<b>Endpt Time</b>	10sec	<b>Result units</b>	% wt/wt
<b>Anode Reagent</b>		<b>Source and date</b>	TW(158)
<b>Cathode Reagent</b>		<b>Cross-reference log</b>	

Results

<b># of Trials</b>	5	<b>Mean Value</b>	10.34%	<b>C.V.</b>	0.33%
--------------------	---	-------------------	--------	-------------	-------

**Comments**